

FORM PTO-1390
(REV. 11-2000)

U.S. DEPARTMENT OF COMMERCE PATENT AND TRADEMARK OFFICE

ATTORNEY'S DOCKET NUMBER

TRANSMITTAL LETTER TO THE UNITED STATES
DESIGNATED/ELECTED OFFICE (DO/EO/US)
CONCERNING A FILING UNDER 35 U.S.C. 371

Mo-6535/LeA 33,042

U.S. APPLICATION NO. (If known, see 37 CFR 1.5)

To be Assigned

09/913760

INTERNATIONAL APPLICATION NO.

INTERNATIONAL FILING DATE

PCT/EP00/01117

11 February 2000 (11.02.00)

PRIORITY DATE CLAIMED

24 February 1999 (24.02.99)

TITLE OF INVENTION FLAME-RESISTANT THERMOPLASTIC MOULDING MATERIAL

APPLICANT(S) FOR DO/EO/US 1) Axel Brenner; 2) Walter Kohler; 3) Martin Dobler

Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:

1. ☒ This is a **FIRST** submission of items concerning a filing under 35 U.S.C. 371.
2. ☐ This is a **SECOND or SUBSEQUENT** submission of items concerning a filing under 35 U.S.C. 371.
3. ☒ This is an express request to begin national examination procedures (35 U.S.C. 371(f)). The submission must include items (5), (6), (9) and (21) indicated below.
4. ☒ The US has been elected by the expiration of 19 months from the priority date (Article 31).
5. ☒ A copy of the International Application as filed (35 U.S.C. 371(c)(2))
 - a. ☒ is attached hereto (required only if not communicated by the International Bureau).
 - b. ☐ has been communicated by the International Bureau.
 - c. ☐ is not required, as the application was filed in the United States Receiving Office (RO/US).
6. ☒ An English language translation of the International Application as filed (35 U.S.C. 371(c)(2)).
 - a. ☒ is attached hereto.
 - b. ☐ has been previously submitted under 35 U.S.C. 154(d)(4).
7. ☐ Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371(c)(3))
 - a. ☐ are attached hereto (required only if not communicated by the International Bureau).
 - b. ☐ have been communicated by the International Bureau.
 - c. ☐ have not been made; however, the time limit for making such amendments has NOT expired.
 - d. ☐ have not been made and will not be made.
8. ☐ An English language translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371 (c)(3)).
9. ☒ An oath or declaration of the inventor(s) (35 U.S.C. 371(c)(4)).
10. ☐ An English language translation of the annexes of the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371(c)(5)).

Items 11 to 20 below concern document(s) or information included:

11. ☐ An Information Disclosure Statement under 37 CFR 1.97 and 1.98.
12. ☒ An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.
13. ☒ A **FIRST** preliminary amendment.
14. ☐ A **SECOND or SUBSEQUENT** preliminary amendment.
15. ☐ A substitute specification.
16. ☐ A change of power of attorney and/or address letter.
17. ☐ A computer-readable form of the sequence listing in accordance with PCT Rule 13ter.2 and 35 U.S.C. 1.821 - 1.825.
18. ☒ A second copy of the published international application under 35 U.S.C. 154(d)(4).
19. ☐ A second copy of the English language translation of the international application under 35 U.S.C. 154(d)(4).
20. ☒ Other items or information:

Preliminary Amendment w/Abstract; PTO Form 1449 and references listed therein

U.S. APPLICATION NO. 00/913760 To be Assigned		INTERNATIONAL APPLICATION NO. PCT/EP00/01117		ATTORNEY'S DOCKET NUMBER Mo-6535/LeA 33,042	
---	--	--	--	---	--

21. <input checked="" type="checkbox"/> The following fees are submitted: BASIC NATIONAL FEE (37 CFR 1.492 (a) (1) - (5)): Neither international preliminary examination fee (37 CFR 1.482) nor international search fee (37 CFR 1.445(a) (2)) paid to USPTO and International Search Report not prepared by the EPO or JPO \$1000.00 International preliminary examination fee (37 CFR 1.482) not paid to USPTO but International Search Report prepared by the EPO or JPO \$860.00 International preliminary examination fee (37 CFR 1.482) not paid to USPTO but international search fee (37 CFR 1.445(a)(2)) paid to USPTO \$710.00 International preliminary examination fee (37 CFR 1.482) paid to USPTO but all claims did not satisfy provisions of PCT Article 33(1)-(4) \$690.00 International preliminary examination fee (37 CFR 1.482) paid to USPTO and all claims satisfied provisions of PCT Article 33(1)-(4) \$100.00 ENTER APPROPRIATE BASIC FEE AMOUNT =				CALCULATIONS PTO USE ONLY	
				\$	860.00
Surcharge of \$130.00 for furnishing the oath or declaration later than <input type="checkbox"/> 20 <input type="checkbox"/> 30 months from the earliest claimed priority date (37 CFR 1.492(e)).				\$	
CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE	\$	
Total claims	24 -20 =	4	x \$18.00	\$	72.00
Independent claims	3 -3 =	0	x \$80.00	\$	0.00
MULTIPLE DEPENDENT CLAIM(S) (if applicable)				\$	
				\$	
TOTAL OF ABOVE CALCULATIONS =				\$	932.00
<input type="checkbox"/> Applicant claims small entity status. See 37 CFR 1.27. The fees indicated above are reduced by 1/2.				\$	
SUBTOTAL =				\$	932.00
Processing fee of \$130.00 for furnishing the English translation later than <input type="checkbox"/> 20 <input type="checkbox"/> 30 months from the earliest claimed priority date (37 CFR 1.492(f)).				\$	
TOTAL NATIONAL FEE =				\$	932.00
Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31). \$40.00 per property +				\$	40.00
TOTAL FEES ENCLOSED =				\$	972.00
				Amount to be refunded:	\$
				charged:	\$

a. ☐ A check in the amount of \$ _____ to cover the above fees is enclosed.


b. ☒ Please charge my Deposit Account No. 13-3848 in the amount of \$ 972.00 to cover the above fees.
 A duplicate copy of this sheet is enclosed.

c. ☒ The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any
 overpayment to Deposit Account No. 13-3848. A duplicate copy of this sheet is enclosed.

d. ☐ Fees are to be charged to a credit card. **WARNING:** Information on this form may become public. **Credit card
 information should not be included on this form.** Provide credit card information and authorization on PTO-2038.

NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR
 1.137 (a) or (b)) must be filed and granted to restore the application to pending status.

SEND ALL CORRESPONDENCE TO:



00157

PATENT TRADEMARK OFFICE

SIGNATURE _____

Aron Preis
NAME

29,426
REGISTRATION NUMBER

001093760
JC03 Rec'd PCT/PTC 17 AUG 2001

PATENT APPLICATION
Mo-6535
LeA 33,042

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

APPLICATION OF)
AXEL BRENNER ET AL) PCT/EP00/01117
SERIAL NUMBER: TO BE ASSIGNED)
FILED: HEREWITH)
TITLE: FLAME-RESISTANT THERMO-)
PLASTIC MOULDING MATERIAL)

PRELIMINARY AMENDMENT

Assistant Commissioner for Patents
Washington, D.C. 20231

Sir:


Prior to its examination kindly amend the English language translation of the enclosed application as follows:

"Express Mail" mailing label number ET146885751US
Date of Deposit August 17, 2001

I hereby certify that this paper or fee is being deposited with the United States Postal Service "Express Mail Post Office to Addressee" service under 37 CFR 1.10 on the date indicated above and is addressed to the Assistant Commissioner of Patents and Trademarks, Washington, D.C. 20231

Donna J. Veatch

(Name of person mailing paper or fee)


Signature of person mailing paper or fee)

IN THE SPECIFICATION:

Please delete the title of the application appearing in page 1 and insert therefor
-- FLAME-RESISTANT THERMOPLASTIC MOLDING MATERIAL--.

IN THE ABSTRACT:

Please add the following abstract:

--FLAME-RESISTANT THERMOPLASTIC MOLDING MATERIAL

ABSTRACT OF THE DISCLOSURE


A flame retardant thermoplastic molding composition is disclosed. The composition contains an amorphous thermoplastic polymer, at least one flame retardant in the form of a fully or partially halogenated sulfonic acid salt and at least one alkaline earth metal sulfate and/or one oxide having an average particle size of up to 400 nm.--

IN THE CLAIMS:

Please cancel Claims 1, 11 and 13.

Please amend the following claims to read as follows:

2. (Amended) Molding composition according to Claim 14, characterized in that the alkaline earth metal sulfate and/or oxide is selected from among MgSO_4 , CaSO_4 , SrSO_4 , BaSO_4 , GeO_2 , PbO , PbO_2 , CeO_2 , Ce_2O_3 , SnO , SnO_2 , ZnO , TiO_2 , SiO_2 , ZrO_2 , HfO_2 , Al_2O_3 , Sc_2O_3 , La_2O_3 , and Fe_2O_3 .
3. (Amended) Molding composition according to Claim 2, characterized in that the alkaline earth metal sulfate is barium sulfate.
4. (Amended) The molding composition according to Claim 14, characterized in that the alkaline earth metal sulfate and/or oxide in each case has an average particle size of up to 200 nm.

- 
5. (Amended) The molding composition according to Claim 14, characterized in that the alkaline earth metal sulfate and/or oxide is present in a quantity of from 0.001 to 5.0 wt.% in relation to the total weight of the molding composition.
6. (Amended) The molding composition according to Claim 14, characterized in that the quantity of the flame retardant is from 0.001 to 5.0 wt.% in relation to the total weight of the molding composition.
7. (Amended) The molding composition according to Claim 14, additionally comprising at least one fluorinated hydrocarbon.
8. (Amended) The molding composition according to Claim 7, characterized in that the quantity of the fluorinated hydrocarbons is from 0.001 to 0.5 wt.% in relation to the total weight of the molding composition.
9. (Amended) Process for the preparation of a molding composition according to Claim 14, characterized in that flame retardant and alkaline earth metal sulfate and/or oxide as well as optionally fluorinated hydrocarbon are mixed with the thermoplastic polymers which are to be equipped to be flame-resistant.
10. (Amended) Molded body comprising the thermoplastic molding composition according to Claim 14.
12. (Amended) Process for the production of a molded body according to Claim 10, characterized in that the molding composition is processed by extrusion or injection molding to form molded bodies.

Add the following new claims:

- 14. A thermoplastic molding composition comprising an amorphous thermoplastic polymer, at least one flame retardant in the form of a sulfonic acid salts corresponding to the general formula (I)



in which

15. The composition of Claim 14, wherein said sulfonic acid salt is halogenated.
16. The composition of Claim 14, wherein said sulfonic acid salt is at least partially fluorinated.
17. A thermoplastic molding composition comprising an amorphous thermoplastic polymer, at least one flame retardant corresponding to the general formula (I)

in which

M is any cation, and

at least one alkaline earth metal sulfate and/or one oxide having an average particle size of up to 400 nm.

19. The composition of Claim 17, wherein the flame retardant is at least partially fluorinated.
20. The molding composition of Claim 17, wherein the alkaline earth metal sulfate and/or oxide is selected from the group consisting of MgSO_4 , CaSO_4 , SrSO_4 , BaSO_4 , GeO_2 , PbO , PbO_2 , CeO_2 , Ce_2O_3 , SnO , SnO_2 , ZnO , TiO_2 , SiO_2 , ZrO_2 , HfO_2 , Al_2O_3 , Sc_2O_3 , La_2O_3 and Fe_2O_3 .
21. The molding composition of Claim 20, wherein the alkaline earth metal sulfate is barium sulfate.
22. The molding composition of Claim 17, wherein the alkaline earth metal sulfate and/or oxide has an average particle size of approximately 5 to 40 nm.
23. The molding composition of Claim 17, wherein the alkaline earth metal sulfate and/or oxide is present in a quantity of from 0.001 to 2.0 wt.% in relation to the total weight of the composition.
24. The molding composition of Claim 17, wherein the quantity of the flame retardant is from 0.05 to 0.5 wt.%, in relation to the total weight of the composition.
25. The molding composition of Claim 17, further comprising polytetrafluoroethylene.
26. The molding composition of Claim 25, wherein the quantity of the polytetrafluoroethylene is from 0.001 to 0.5 wt.% in relation to the total weight of the composition.
27. A molded article comprising the composition of Claim 17. --

REMARKS

The present amendment seeks to place the application in better conformance with U.S. practice. A page containing a revised abstract of the disclosure is enclosed.

Entry of the amendment is requested.

Respectfully submitted,

By



Aron Preis
Attorney for Applicants
Reg. No. 29,426

Bayer Corporation
100 Bayer Road
Pittsburgh, Pennsylvania 15205-9741
(412) 777-8343
FACSIMILE PHONE NUMBER:
(412) 777-8363

s:/sr/ap0194

VERSION WITH MARKINGS TO SHOW CHANGES MADE

IN THE SPECIFICATION:

Please delete the title of the application appearing in page 1 and insert therefor
-- FLAME-RESISTANT THERMOPLASTIC MOLDING MATERIAL--.

IN THE ABSTRACT:

Please add the following abstract:

--FLAME-RESISTANT THERMOPLASTIC MOLDING MATERIAL

ABSTRACT OF THE DISCLOSURE

A flame retardant thermoplastic molding composition is disclosed. The composition contains an amorphous thermoplastic polymer, at least one flame retardant in the form of a fully or partially halogenated sulfonic acid salt and at least one alkaline earth metal sulfate and/or one oxide having an average particle size of up to 400 nm.--

IN THE CLAIMS:

Please cancel Claims 1, 11 and 13.

Please amend the following claims:

2. (Amended) Molding [Moulding] composition according to [c]Claim [1]14, characterized [characterised] in that the alkaline earth metal sulfate and/or oxide is selected from among MgSO_4 , CaSO_4 , SrSO_4 , BaSO_4 , GeO_2 , PbO , PbO_2 , CeO_2 , Ce_2O_3 , SnO , SnO_2 , ZnO , TiO_2 , SiO_2 , ZrO_2 , HfO_2 , Al_2O_3 , Sc_2O_3 , La_2O_3 , and Fe_2O_3 .
3. (Amended) Molding [Moulding] composition according to [c]Claim 2, characterized [characterised] in that the alkaline earth metal sulfate is barium sulfate.

4. (Amended) [Moulding] The molding composition according to [c]Claim [1,] 14, characterized [characterised] in that the alkaline earth metal sulfate and/or oxide in each case has an average particle size of up to 200 nm [, in particular approximately 5 to 40 nm].
5. (Amended) [Moulding] The molding composition according to [c]Claim [1,] 14, characterized [characterised] in that the alkaline earth metal sulfate and/or oxide is present in a quantity of from 0.001 to 5.0 wt.% [, in particular up to 2.0 wt.%,] in relation to the total weight of the [moulding] molding composition.
6. (Amended) [Moulding] The molding composition according to [c]Claim [1,] 14, characterized [characterised] in that the quantity of the flame retardant [utilised] is from 0.001 to 5.0 wt.% [, in particular 0.05 to 0.5 wt.%,] in relation to the total weight of the [moulding] molding composition.
7. (Amended) [Moulding] The molding composition according to [c]Claim [1,] 14, [characterised in that the composition comprises] additionally comprising at least one fluorinated hydrocarbon [such as polytetrafluoroethylene].
8. (Amended) [Moulding] The molding composition according to [c]Claim 7, characterized [characterised] in that the quantity of the fluorinated hydrocarbons is from 0.001 to 0.5 wt.% [, in particular 0.01 to 0.1 wt.%,] in relation to the total weight of the [moulding] molding composition.
9. (Amended) Process for the preparation of a molding [moulding] composition according to [one of claims 1 to 8,] Claim 14 characterized [characterised] in that flame retardant and alkaline earth metal sulfate and/or oxide as well as optionally fluorinated hydrocarbon are mixed with the thermoplastic polymers which are to be equipped to be flame-resistant.

10. (Amended) [Moulded] Molded body comprising [produced with the use of] the thermoplastic molding [moulding] composition according to [one of claims 1 to 8] Claim 14.
12. (Amended) Process for the production of a molded [moulded] body according to [c]Claim 10, characterized [characterised] in that the molding [moulding] composition is processed by extrusion or injection molding [moulding] to form molded [moulded] bodies.

Please add the following new claims:

- 14. A thermoplastic molding composition comprising an amorphous thermoplastic polymer, at least one flame retardant in the form of a sulfonic acid salts corresponding to the general formula (I)



in which

R is a straight-chain or branched aliphatic radical having 1 to 30 carbon atoms or an aromatic radical having 6 to 30 carbon atoms, M is a cation, and n is a number corresponding to the valence of M, and at least one alkaline earth metal sulfate and/or one oxide having an average particle size of up to 400 nm .

15. The composition of Claim 14, wherein said sulfonic acid salt is halogenated.
16. The composition of Claim 14, wherein said sulfonic acid salt is at least partially fluorinated.
17. A thermoplastic molding composition comprising an amorphous thermoplastic polymer, at least one flame retardant corresponding to the general formula (I)



in which

R is a straight-chain or branched aliphatic radical having 1 to 30 carbon atoms or an aromatic radical having 6 to 30 carbon atoms ,

M is any cation, and

n is a number corresponding to the valence of M, and

at least one alkaline earth metal sulfate and/or one oxide having an average particle size of up to 400 nm.

18. The composition of Claim 17, wherein the flame retardant is at least partially halogenated.
19. The composition of Claim 17, wherein the flame retardant is at least partially fluorinated.
20. The molding composition of Claim 17, wherein the alkaline earth metal sulfate and/or oxide is selected from the group consisting of MgSO_4 , CaSO_4 , SrSO_4 , BaSO_4 , GeO_2 , PbO , PbO_2 , CeO_2 , Ce_2O_3 , SnO , SnO_2 , ZnO , TiO_2 , SiO_2 , ZrO_2 , HfO_2 , Al_2O_3 , Sc_2O_3 , La_2O_3 and Fe_2O_3 .
21. The molding composition of Claim 20, wherein the alkaline earth metal sulfate is barium sulfate.
22. The molding composition of Claim 17, wherein the alkaline earth metal sulfate and/or oxide has an average particle size of approximately 5 to 40 nm.

23. The molding composition of Claim 17, wherein the alkaline earth metal sulfate and/or oxide is present in a quantity of from 0.001 to 2.0 wt.% in relation to the total weight of the composition.
24. The molding composition of Claim 17, wherein the quantity of the flame retardant is from 0.05 to 0.5 wt.%, in relation to the total weight of the composition.
25. The molding composition of Claim 1, further comprising polytetrafluoroethylene.
26. The molding composition of Claim 25, wherein the quantity of the polytetrafluoroethylene is from 0.001 to 0.5 wt.% in relation to the total weight of the composition.
27. A molded article comprising the composition of Claim 17.--

00/913760

JCO3 Rec'd POT/PTO 17 AUG 2001

Mo-6535
LeA 33,042

-32-

FLAME-RESISTANT THERMOPLASTIC MOLDING MATERIAL

ABSTRACT OF THE DISCLOSURE

A flame retardant thermoplastic molding composition is disclosed. The composition contains an amorphous thermoplastic polymer, at least one flame retardant in the form of a fully or partially halogenated sulfonic acid salt and at least one alkaline earth metal sulfate and/or one oxide having an average particle size of up to 400 nm.

00/913760

I hereby certify that this paper or fee is being deposited with the United States Postal Service "Express Mail Post Office to Addressee" service under 37 CFR 1.10 on the date indicated above and is addressed to the Assistant Commissioner of Patents and Trademarks, Washington, D.C. 20231

Donna J. Veatch

(Name of person mailing paper or fee)



Signature of person mailing paper or fee)

Flame-resistant thermoplastic moulding compositionJC03 Rec'd 09/913760
PCT/PTO 17 AUG 2001

The invention relates to a flame-resistant thermoplastic moulding composition which comprises an amorphous thermoplastic polymer and a flame retardant, and flame-resistant moulded bodies produced therefrom.

The flame behaviour of amorphous thermoplastics such as polycarbonates plays an important role in particular in areas in which compliance with specific fire safety regulations is a requirement, such as in the electrical, automotive, construction and aeronautical sectors. UL-94, the Underwriters Laboratories flammability test (Underwriters Laboratories, Northbrook, Illinois, USA) which considers both the burning duration of the plastic following flame impingement and also the tendency to drip burning material, is the standard frequently applied to flammability of solid plastics. In accordance with the UL-94 regulation a flame impinges under specified conditions on plastic samples of variable thickness measuring 12.7 x 1.27 cm, and the burning duration is determined. The samples are classified into UL-94 flammability classes V0, V1 and V2, in order of decreasing flame resistance. In order to be classified into UL-94 flammability class V0 a sample must not exceed a specified burning duration, and additionally a surgical cotton wad located beneath the sample must not be ignited by dripping burning particles.

Flame retardants are utilised for the preparation of flame-resistant amorphous thermoplastics such as polycarbonates. They are generally known and are described, for example, in B.J. Sutker "Flame Retardants", Ullmann's Encyclopedia of Industrial Chemistry, 6th edition, 1998.

There is a need for mouldings made of flame-resistant amorphous thermoplastics, which meet the requirements of UL-94 flammability class V0 even at relatively low wall thicknesses. Thus in the case of electrical equipment weight savings can be achieved by the use of polycarbonate housings having the thinnest possible walls, for instance. There is furthermore a need for thin-walled mouldings of amorphous thermoplastics which in addition to having excellent flame retardant properties are

LA 33 042

- 2 -

transparent. Transparent polycarbonate mouldings have a role in, for instance, housings and covering plates for electrical equipment as well as in the construction sector for sheets, windows and claddings of widely varying types.

5 EP 0 531 861 A1 discloses the equipping of polycarbonates with a halogen-free sulfonic acid salt of aromatic aldehydes or acetal derivatives thereof, optionally in combination with inorganic sulfates such as sodium or potassium sulfate as fire retardants. The use of these fire retardants enables UL-94 flammability class V0 to be achieved for 3.2 mm-thick polycarbonate test specimens. Test specimens having a
10 lesser thickness do not achieve UL-94 flammability class V0.

EP 0 362 623 A2 further discloses flame-retarded polyethylene terephthalate moulding compositions achieving good crystallisation, which comprise from 1 to 25 wt.% polyalkyl phosphonates as flame retardants as well as from 0.01 to 10 wt.%
15 ultra-fine barium sulfate in combination with from 0.01 to 5 wt.% fluorinated polyolefins as crystallisation promoters. The fluorinated polyolefin content enables only cloudy mouldings to be produced from the polyethylene terephthalate moulding compositions described.

20 A disadvantage of the known flame retardants is that UL-94 flammability class V0 can be achieved in respect of polycarbonate only at moulding wall thicknesses of 3.2 mm or more. The known flame retardants furthermore tend to cloud the thermoplastic moulding compositions and/or they are subject to frequent fluctuations in their flame-retardant effect. A further disadvantage is the frequent marked
25 impairment, caused by the recycling process, of the flame-retardant effect of mouldings equipped with known flame retardants. Mouldings processed by shredding and re-extrusion of scrap to form recycled mouldings therefore frequently have a substantially poorer flame behaviour than the original mouldings. What is more, a range of known flame retardants are sensitive to compromising of their
30 effectiveness by the presence of mould release agents such as glycerol monostearate (GMS) or pentaerythritol tetrastearate (PETS). Known flame retardants frequently

- 3 -

require the use of additional transesterification catalysts in order to deploy their effect, potentially leading to undesirable changes in the properties of the plastic.

The object of the invention is to provide amorphous thermoplastic moulding compositions, in particular those such as are of polycarbonate, having improved flame behaviour. The moulding compositions should still achieve UL-94 flammability class V0 even at wall thicknesses of less than 3.2 mm. This should occur if possible with no deterioration in the transparency and mechanical properties of the moulding compositions. The moulding compositions should furthermore also still afford the desired flame retardancy as a recycled product. The flame retardancy should not furthermore be impaired by the use of mould release agents such as GMS or PETS. The moulding compositions should furthermore be preparable without the use of additional transesterification catalysts which lead to undesirable changes in the properties.

This object is achieved according to the invention by a thermoplastic moulding composition which comprises an amorphous thermoplastic polymer and a flame retardant in combination with an alkaline earth metal sulfate and/or an oxide having in each case an average particle size of up to 400 nm. The alkaline earth metal sulfates and oxides used according to the invention having an average particle size of up to 400 nm are also designated hereinbelow "nanoparticulate" or "ultra-fine" alkaline earth metal sulfates and oxides.

The moulding composition which comprises an amorphous thermoplastic polymer in particular includes as a flame retardant a mixture of a known flame retardant selected from among sulfonic acid salts, sulfonamide acid salts, organic phosphates and salts thereof, halogenated benzoic acid ester salts and hexafluoroaluminates and an alkaline earth metal sulfate and/or an oxide having in each case an average particle size of up to 400 nm.

According to an embodiment of the invention the moulding composition according to the invention further comprises a fluorinated hydrocarbon such as polytetrafluoroethylene.

5 It was here surprisingly found that flame-resistant thermoplastic moulding compositions having an extremely favourable property profile can be prepared by the addition of nanoparticulate alkaline earth metal sulfates and/or oxides in addition to the known flame retardants. The mouldings according to the invention thus still achieve UL-94 flammability class V0 even at a wall thickness of 0.8 mm and, at a
10 thickness of up to 2.8 mm, pass the Underwriters Laboratories UL-94 5V bar test.

The use of nanoparticulate alkaline earth metal sulfates and/or oxides enables the quantity of known flame retardants which is required in order to achieve a specified flame-retardant effect to be reduced. This means that less flame retardant needs to be
15 utilised as a result of the utilisation of nanoparticulate alkaline earth metal sulfates and/or oxides, with the same flame-retardant effect.

The addition of nanoparticulate alkaline earth metal sulfates and/or nanoparticulate oxides is able to improve markedly the flame-retardant effect of known flame retardants despite neither of the compound classes first named having alone any flame-retardant effect. This means that the combination of known flame retardant and nanoparticulate alkaline earth metal sulfates/oxides deploys a synergistic effect with respect to the flame-retardant properties of the thermoplastic moulding compositions.
20

25 The mechanical properties of the thermoplastic moulding compositions according to the invention are not influenced disadvantageously by the presence of nanoparticulate alkaline earth metal sulfates and/or oxides and are good even after recycling of the moulding compositions. Thus the moulding compositions according to the invention are distinguished, both before and after recycling, by a high notched impact strength in accordance with ISO 180-4a, for example.
30

- 5 -

An essential advantage of the invention resides furthermore in the ability of the mouldings also to be produced as highly transparent mouldings. This has significance in particular in the case of plastic mouldings such as plastic windows, which are used in the construction sector, as well as in the case of housings and covering plates for electrical equipment. UL-94 flammability class V0 can be achieved in respect of the transparent mouldings according to the invention at a wall thickness of up to 2.4 mm. Furthermore, regenerated products from mouldings equipped with the additives described herein still have a high flame resistance and a low tendency to drip burning material.

In moulding compositions destined for the production of transparent mouldings, the alkaline earth metal sulfates and/or oxides preferably have an average particle size of less than approximately 100 nm, still more preferably approximately 5 to 40 nm. The particle size can be determined by ultra-centrifuging as reported by Langer, H. "Particle and Particle Size Characterization", Vol. 12, p. 148, 1995, for example.

Alkaline earth metal sulfates which are utilisable according to the invention are, for example, magnesium sulfate, calcium sulfate, strontium sulfate and barium sulfate. Mixtures of different alkaline earth metal sulfates may also be utilised.

According to a particularly preferred embodiment of the invention nanoparticulate barium sulfate is used. This may, as described in EP 335 159 A1, for example, be prepared by combining separate aqueous solutions which comprise respectively equimolar quantities of barium ions and sulfate ions, for instance as a result of combining equimolar solutions of barium chloride and sodium sulfate, followed by separation of the precipitate. In order to obtain a primary grain size of less than 0.1 μm , the respective aqueous solutions are brought together rapidly in continuous manner, in each case in drop form having an average drop size of less than approximately 0.5 μl , and the precipitation is induced in rapid and complete manner in a total volume of less than approximately 1 μl .

- 6 -

All oxides which are preparable having an average particle size of up to approximately 400 nm may be used as the oxides. These are in particular those such as belong to groups 2b, 3a, 3b, 4a, 4b and 8b of the Periodic Table as well as oxides of the lanthanides and actinides. Oxides which are preferred according to the invention are GeO_2 , PbO , PbO_2 , CeO_2 , Ce_2O_3 , SnO , SnO_2 , ZnO , TiO_2 , SiO_2 , ZrO_2 , HfO_2 , Al_2O_3 , Sc_2O_3 , La_2O_3 and Fe_2O_3 . Mixtures of different oxides may also be utilised.

The quantity of alkaline earth metal sulfates and/or oxides in the moulding composition may be varied within broad limits. However, at above 10 wt.%, in relation to the total weight of the moulding composition, undesirable changes occur in the physical properties of the moulding compositions, while when additive quantities are less than 0.0005 wt.% no appreciable flame retardancy-reinforcing effect takes place. Since the flame retardancy-reinforcing effect is already achieved at very low additive quantities, the alkaline earth metal sulfates and/or oxides are preferably utilised in quantities of from 0.001 to 5.0 wt.%, and even more preferably from 0.01 to 2.0 wt.%, in relation to the total weight of the moulding composition.

The synergistic effect of the nanoparticulate alkaline earth metal sulfates and/or oxides with respect to the flame-retardant properties of the moulding compositions occurs in combination with numerous known flame retardants. These include both halogen-containing and also halogen-free compounds. Suitable halo-compounds are organic fluorine, chlorine and/or bromine compounds which are stable during the preparation and processing of the moulding compositions according to the invention, such that no corrosive gases are liberated and their effectiveness is not impaired. Mixtures of known flame retardants may also be utilised.

The quantity of the flame retardants utilised may be varied within broad limits and is strongly dependent on the desired flame-retardant properties of the plastic and on the type of flame retardant used. Preferably from 0.001 to 5.0 wt.%, in particular 0.05 to 0.5 wt.% flame retardant, in relation to the total weight of the moulding composition, is utilised.

Flame retardants which are particularly preferred according to the invention are sulfonic acid salts, sulfonic acid amide salts, organic phosphates and salts thereof, halogenated benzoic acid ester salts and/or hexafluoroaluminates.

Sulfonic acid salts which are particularly suitable are those corresponding to the general formula (I)



in which

R is a straight-chain or branched aliphatic radical having 1 to 30 carbon atoms or an aromatic radical having 6 to 30 carbon atoms which may be fully or partially halogenated,

M is any cation, and n is a number corresponding to the valency of M.

These are described, for instance, in US 4 239 678. Fully or partially fluorinated sulfonic acid salts corresponding to the general formula (I) are particularly preferred. Sodium or potassium perfluorobutane sulfonate, sodium or potassium perfluoromethane sulfonate, sodium- or potassium-2,5-dichlorobenzene sulfonate, sodium- or potassium-2,4,5-trichlorobenzene sulfonate, sodium or potassium diphenylsulfone sulfonate and sodium- or potassium-2-formylbenzene sulfonate might be named by way of example. According to a particularly preferred embodiment of the invention potassium perfluorobutane sulfonate is utilised as a flame retardant.

Particularly suitable flame retardants are furthermore the sulfonic acid amide salts described in US 4 727 101, corresponding to the general formula (II)



- 8 -

in which

Ar is an aromatic radical and R is a monovalent aliphatic radical, or

Ar and R together form a bivalent aromatic radical,


M is any cation, and

n corresponds to the valency of M.

Particularly preferred sulfonic acid amide salts are sodium and potassium (N-benzenesulfonyl) benzene sulfonamide.

Aromatic sulfonic acid salts are furthermore considered as flame retardants. These are in particular the metal salts of monomeric or polymeric aromatic sulfonic acids, as described in US 3 940 366 and US 3 933 734 and the sulfonic acid salts of monomeric and polymeric aromatic carboxylic acids and esters thereof, as disclosed in US 3 953 399, as well as the sulfonic acid salts of aromatic ketones, as described in US 3 926 908 and US 4 104 246.

Particularly suitable aromatic sulfonic acid salts are furthermore the halogen-free sulfonic acid salts of aromatic aldehydes or acetals thereof, as described in US 5 356 965. These are in particular those such as correspond to the general formula (III):



in which

Ar is an aromatic radical having 1 to 4 aromatic rings,

M stands for a metal from groups 1a, 1b, 2a or 2b of the Periodic Table of Elements,

5

R is hydrogen, a halogen-free C_1 - C_6 -alkyl, a halogen-free C_6 - C_{10} -aryl, a halogen-free C_1 - C_6 -alkoxy, a halogen-free acylamino group or a halogen-free acylimino group, and

10 X stands for oxygen or a halogen-free polyvalent group having the structure $R'(-O-)_{2-6}$ or for two halogen-free monovalent $R'-O$ -radicals,

wherein

15 R' is an optionally branched, halogen-free C_2 - C_{20} -alkyl or -alkylene, halogen-free C_5 - C_{10} -aryl or -arylene or halogen-free C_7 - C_{20} -aralkyl or -aralkylene radical, which optionally links a plurality of structural units (III).

20 The sulfonic acid salts according to the invention are derived from aromatic sulfonic acids which carry aldehyde groups, which are readily prepared by known methods, for example from the base aldehydes by sulfonation, from aromatic haloaldehydes by exchanging the halogen for the sulfonate group or from the sulfonates by formylation. The flame-retardant effect is exerted both by the aldehydes themselves
25 and also by their acetal derivatives which are obtainable by acid-catalysed reaction with alcohols or phenols with separation of water. When monoalcohols are used the acyclic acetates having two radicals R' per aldehyde group arise; from diols or orthodiphenols the simple cyclic acetates arise; when tri- or tetraalcohols or tri- or tetraphenols are used, two aldehyde groups are in each case linked together by way
30 of the alcohol radical or phenol radical. If more than one aldehyde group is comprised in the aromatic sulfonate, or more than two hydroxy groups are

comprised in the alcohol or phenol used for the acetalisation, the corresponding acetates may also be oligomeric or polymeric in type.

For example, the following compounds may be utilised in the form of their metal

5 salts as aldehyde group-containing sulfonates: 2-formylbenzenesulfonic acid, 3-formylbenzenesulfonic acid, 4-formylbenzenesulfonic acid, 5-formyl-2-methylbenzenesulfonic acid, 5-formyl-2-methoxybenzenesulfonic acid, 5-formyl-2-hexadecyloxybenzenesulfonic acid, 2-formylbenzene-1,5-disulfonic acid, 2,4-diformylbenzenesulfonic acid, 2-formyl-5-phenylbenzenesulfonic acid, biphenyl-4'-
10 formyl-4-sulfonic acid, biphenyl-4,4'-bis-formyl-2,2'-disulfonic acid, 2-formyl-5-phenylbenzenesulfonic acid, biphenyl-4'-formyl-4-sulfonic acid, biphenyl-4,4'-bis-formyl-2,2'-disulfonic acid, 2-formyl-5-(acetylamino)benzenesulfonic acid or 2-formyl-5-(phthalimino)benzenesulfonic acid, or acetates thereof which are obtainable, for example, by reacting the aforementioned aldehydes with the
15 following hydroxy compounds: methanol, ethanol, n-propanol, n-butanol, isobutyl alcohol, isopentyl alcohol, 2-ethylhexanol, benzyl alcohol, 2-phenylethanol, 3-phenyl-1-propanol, ethylene glycol, propylene glycol, 1,3-propanediol, 1,2-butylene glycol, 1,3-butanediol, 2,3-butanediol, neopentyl glycol, 2,5-hexanediol, 2-methyl-2-propyl-1,3-propanediol, 2,2-diethyl-1,3-propanediol, glycerol, 2-hydroxymethyl-
20 2-methyl-1,3-propanediol, 1,1,1-trimethylolpropane, pentaerythritol, sorbitol, mannitol, 1,2-cyclohexanediol, 1,4-cyclohexane dimethanol, bis-hydroxymethyl-hexahydro-4,7-methanoindane, catechol, 1,4-bis(2-hydroxyethoxy) benzene, 4-tert.-butylcatechol, 2,3-naphthalenediol, 1,8-naphthalenediol, 2,2'-dihydroxybiphenyl, 3,4-dihydroxybiphenyl, 2,2-bis(4-hydroxyphenyl) propane, 2,2-bis(4-(2-hydroxyethoxy)phenyl) propane or 2,2-bis(4-(2,3-dihydroxypropoxy)phenyl) propane
25 propane, glycerol-1-phenylether, glycerol-1-(nonylphenyl) ether, glycerol-1-(p-cumylphenyl) ether, 2,2-bis(4-(2,3-dihydroxypropoxy)phenyl) propane and stearyl alcohol.

30 The metal cation of the sulfonates may come from groups 1a,b or 2a,b of the Periodic Table. In particular lithium, sodium, potassium, magnesium, calcium and zinc are considered. Alkali metals and alkaline earth metals are preferred.

5 The sulfonic acid salts content according to the invention of the thermoplastic moulding composition may be varied within broad limits. However, at above 10 wt.% undesirable changes occur in the physical properties of the moulding composition, while the flame-retardant effect is lost at additive quantities of less than 0.005 wt.%. Because the flame-retardant effect is already achieved with very low additive quantities, the sulfonic acid salts according to the invention are preferably added in quantities of between 5 and 0.01 wt.%.

10 All phosphorus compounds conventionally used for this purpose, in particular phosphine oxides and derivatives of acids of phosphorus and salts of acids and acid derivatives of phosphorus, are likewise preferably suitable as the flame retardant.

15 Derivatives (for example esters) of acids of phosphorus and salts thereof are preferably utilised, with acids of phosphorus including phosphoric acid, phosphonic acid, phosphinic acid, phosphorous acid, including in each case in dehydrated form, salts are preferably alkali metal, alkaline earth metal and ammonium salts of these acids, and derivatives thereof (for example partially esterified acids) are also included.

20 Phosphoric acid ester salts corresponding to the general formula (IV)



25 in which

M is any metal,

30 R is a straight-chain or branched aliphatic radical having 1 to 30 carbon atoms or an aromatic radical having 6 to 30 carbon atoms, in which the hydrogen atoms may be fully or partially halogenated, and $a+b = 3$,


- 12 -

are furthermore particularly suitable.

Preferred examples of such compounds are sodium or potassium methyl phosphonate, sodium or potassium-(2-phenylethylene) phosphonate and lithium phenyl phosphonate.

Further preferred organic phosphorus compounds are the phosphoric acid semiesters described in US 4 495 111.

Preferred organic phosphorus compounds are furthermore those such as correspond to the general formula (V)



in which

R^{12} , R^{13} and R^{14} are independently of one another an optionally halogenated C_1 - C_8 -alkyl or an optionally halogenated and/or alkylated C_5 - or C_6 -cycloalkyl or an optionally halogenated and/or alkylated and/or aralkylated C_6 - C_{30} -aryl, and

N and M are independently of one another 0 or 1.


These phosphorus compounds are generally known and are described, for example, in Ullmann, "Enzyklopädie der technischen Chemie" [Encyclopedia of Industrial Chemistry], Vol. 18, pp. 301 et seq., 1979. The aralkylated phosphorus compounds are described, for example, in DE-OS 38 24 356.

- 13 -

The optionally halogenated and/or alkylated and/or aralkylated C₆-C₃₀-aryl radicals in the formula (V) are optionally mono- or polynuclear, have single or multiple halogenation and/or alkylation and/or aralkylation, for example chlorophenyl, bromophenyl, pentachlorophenyl, pentabromophenyl, phenyl, cresyl, isopropylphenyl, benzyl-substituted phenyl and naphthyl.

Phosphorus compounds corresponding to the formula (V) which are utilisable according to the invention are, for example, tributyl phosphate, tris(2-chloroethyl) phosphate, tris(2,3-dibromopropyl) phosphate, triphenyl phosphate, tricresyl phosphate, diphenylcresyl phosphate, diphenyloctyl phosphate, diphenyl-2-ethylcresyl phosphate, tri-(isopropylphenyl) phosphate, tris(p-benzylphenyl) phosphate, triphenyl phosphine oxide, methanephosphonic acid dimethyl ester, methanephosphonic acid diphenyl ester and phenylphosphonic acid diethyl ester.

Suitable flame retardants are furthermore the oligomeric phosphorus compounds described in EP 0 363 608 which correspond to the formula (VI)



in which

R¹⁵, R¹⁶, R¹⁷, R¹⁸ denote independently of one another C₁-C₁₈-alkyl, preferably methyl, C₅-C₆-cycloalkyl, C₆-C₁₀-aryl, preferably phenyl, C₇-C₁₂-aralkyl, preferably phenyl-C₁-C₄-alkyl,

n denotes independently of one another 0 or 1,

- 14 -

N denotes 1 to 5, and

5 X denotes a mono- or polynuclear aromatic radical having 6 to 30 C atom, preferably derived from bisphenol A, hydroquinone or resorcinol.

The molecular weight of the phosphorus compounds corresponding to the formula (VI) is generally less than 2000 g/mol, preferably less than 1000 g/mol.

10 The optionally halogenated C₁-C₈-alkyl radicals in the formulae (V) and (VI) may have single or multiple halogenation and may be linear or branched. Examples of alkyl radicals are chloroethyl, 2-chloropropyl, 2,3-dibromopropyl, butyl, methyl or octyl.

15 The optionally halogenated and/or alkylated C₅- or C₆-cycloalkyl radicals in the formulae (V) and (VI) are C₅- or C₆-cycloalkyl radicals which optionally have single to multiple halogenation and/or alkylation, such as cyclopentyl, cyclohexyl, 3,3,3-trimethylcyclohexyl and perchlorocyclohexyl.

20 In the case of mixtures of a plurality of phosphates corresponding to the formula (VI), N represents an average value between 1 and 5. Preferred flame retardants are also mixtures of phosphorus compounds corresponding to the formula (V) and phosphorus compounds corresponding to the formula (VI).

25 Suitable flame retardants are furthermore halogenated benzoic acid salts such as sodium or potassium pentachlorobenzoate, sodium- or potassium-2,4,6-trichlorobenzoate and sodium- or potassium-2,4-dichlorobenzoate as well as hexafluoroaluminates such as sodium or potassium hexafluoroantimonate.

30 Moreover, halogen-containing flame retardants such as chlorinated and brominated diphenyls such as octachlorodiphenyl, decachlorodiphenyl, octabromodiphenyl, decabromodiphenyl; chlorinated and brominated diphenyl ethers such as octa- and

decachlorodiphenyl ether and octa- and decabromodiphenyl ether; chlorinated and brominated phthalic anhydride and derivatives thereof, such as phthalimides and bisphthalimides, for example tetrachloro- and tetrabromophthalic anhydride, tetrachloro- and tetrabromophthalimide, N,N'-ethylene-bistetrachloro- and N,N'-ethylene-bistetrabromophthalimide, N-methyltetrachloro- and N-methyltetrabromophthalimide; chlorinated and brominated bisphenols such as 2,2-bis(3,5-dichloro-4-hydroxyphenyl) propane and 2,2-bis(3,5-dibromo-4-hydroxyphenyl) propane; 2,2-bis(3,5-dichloro-4-hydroxyphenyl) propane oligocarbonate and 2,2-bis(3,5-dichloro-4-hydroxyphenyl) propane oligocarbonate having an average degree of polycondensation (M_n) of from 2 to 20 may. Bromine compounds are preferred to chlorine compounds.

The moulding compositions may additionally comprise fluorinated hydrocarbons, in particular fluorinated polyolefins, in the case of specific flame retardancy requirements. It has been ascertained according to the invention that these when combined with nanoparticulate alkaline earth metal sulfates and/or nanoparticulate oxides and known flame retardants deploy a synergistic effect with respect to the flame-retardant properties of the thermoplastic moulding compositions. The fluorinated polyolefins which are usable have high molecular weights and glass transition temperatures greater than -30°C , generally greater than 100°C . The fluorine contents of the fluorinated polyolefins are preferably from 65 to 76 wt.%, in particular 70 to 76 wt.%. The average particle diameter d_{50} of the fluorinated polyolefins is from 0.05 to 1000 μm , preferably 0.08 to 20 μm . The density of the fluorinated polyolefins is generally from 1.2 to 2.3 g/cm^3 . Preferred fluorinated polyolefins are polytetrafluoroethylene, polyvinylidene fluoride, tetrafluoroethylene/hexafluoropropylene copolymer and ethylene/tetrafluoroethylene copolymer. Such fluorinated polyolefins are described, for example, in Schildknecht "Vinyl- und Related Polymer" [Vinyl and Related Polymers], John Wiley & Sons, Inc., New York, 1962, pp. 284-494; Wall "Fluoropolymers", Wiley-Interscience, John Wiley & Sons, Inc., New York, Vol. 13, 1970, pp 623-654; "Modern Plastics Encyclopedia", 1970-1971, Vol. 47, No. 10 A, October 1970, McGraw-Hill, Inc., New York, pp. 134 and 774; "Modern Plastics Encyclopedia", 1975-1976, October

1975, Vol. 52, No. 10 A. McGraw-Hill, Inc., New York, pp, 27, 28 and 472 as well as in US 3 671 487, US 3 723 373 and US 3 838 092.

5 The quantity of the fluorinated hydrocarbons to be utilised in the thermoplastic moulding composition is dependent on the desired material properties and may be varied within broad limits. The quantity of the fluorinated polyolefins is preferably from 0.001 to 0.5 wt.%, in particular 0.01 to 0.1 wt.%, in relation to the total weight of the moulding composition.

10 According to a particularly advantageous embodiment of the invention polytetrafluoroethylene is utilised as the fluorinated hydrocarbon. A particularly good flame retardancy behaviour of the moulding composition is obtained with no deterioration of the other material properties when polytetrafluoroethylene is utilised in a quantity of from 0.001 to 0.5 wt.%, in particular 0.01 to 0.1 wt.%, in relation to
15 the total weight of the moulding composition.

Amorphous thermoplastic polymers within the meaning of this invention are all amorphous thermoplastics, in particular amorphous polyesters and amorphous polyolefins as well as in each case, copolymers and polymer blends thereof.

20 Amorphous polyesters to be utilised according to the invention are in particular polycarbonates. Amorphous polyolefins include both open-chain polyolefins such as polypropylene and amorphous polystyrenes as well as cycloolefin polymers.

According to a particularly preferred embodiment of the invention polycarbonates
25 are utilised as the polymers. Polycarbonates which are suitable according to the invention are both homopolycarbonates and also copolycarbonates. A mixture of the polycarbonates which are suitable according to the invention may also be used. The polycarbonates may be replaced partially or completely by aromatic polyester carbonates. The polycarbonates may also comprise polysiloxane blocks. Their
30 preparation is described, for example, in US 3 821 325, US 3 189 662 and US 3 832 419. Other polymers may be admixed to the polycarbonates, thus obtaining so-called polymer blends. For example, blends may be prepared from the polycarbonates

- 17 -

equipped according to the invention and ABS polymers or from the polycarbonates equipped according to the invention to be flame-resistant and polyesters such as polyethylene terephthalate or polybutylene terephthalate.

- 5 The thermoplastic polycarbonates which are to be equipped according to the invention to be flame-resistant have average molecular weights \overline{M}_w of 10,000 to 200,000 g/mol, preferably 15,000 to 45,000 g/mol, still more preferably 18,000 to 35,000 g/mol, determined by measuring the relative viscosity at 25°C in CH_2Cl_2 and at a concentration of 0.5 g per 100 ml CH_2Cl_2 ; they may be straight-chain or
10 branched. Such thermoplastic polycarbonates are known from the literature or are preparable by methods known from the literature.

- For the preparation of polycarbonates reference might be made, for example, to H. Schnell, "Chemistry and Physics of Polycarbonates", Polymer Reviews, Vol. 9, Interscience Publishers, New York, London, Sydney 1964, D.C. Prevorsek, B.T. Debona and Y. Kesten, Corporate Research Center, Allied Chemical Corporation, Morristown, New Jersey 07960, "Synthesis of Poly(ester)carbonate Copolymers" in
15 Journal of Polymer Science, Polymer Chemistry Edition, Vol. 19, 75-90 (1980), D. Freitag, U. Grigo, P.R. Müller, N. Nouvertne, BAYER AG, "Polycarbonates" in Encyclopedia of Polymer Science and Engineering, Vol. 11, second edition, 1988, pp. 648-718, and finally U. Grigo, K. Kircher and P.R. Müller "Polycarbonate" [Polycarbonates], in Becker/Braun, Kunststoff-Handbuch [Manual of Plastics], Vol. 3/1, Polycarbonate, Polyacetale, Polyester, Celluloseester [Polycarbonates, polyacetals, polyesters, cellulose esters], Carl Hanser Verlag, Munich, Vienna 1992,
20 pp. 117-299. They are preferably prepared by the interfacial process, the pyridine process or the melt transesterification process.

- Compounds to be preferably utilised as starting compounds for the preparation of polycarbonates are bisphenols corresponding to the general formula HO-Z-OH , in
30 which Z is a bivalent organic radical having 6 to 30 carbon atoms which comprises one or more aromatic groups. Examples of such compounds are bisphenols belonging to the group comprising the dihydroxydiphenyls, bis(hydroxyphenyl)

alkanes, bis(hydroxyphenyl) cycloalkanes, indane bisphenols, bis(hydroxyphenyl) sulfides, bis(hydroxyphenyl) ethers, bis(hydroxyphenyl) sulfones, bis(hydroxyphenyl) sulfoxides, bis(hydroxyphenyl) ketones and α,α' -bis(hydroxyphenyl) diisopropylbenzenes.

5

Preferred bisphenols belonging to the aforementioned groups of compounds are hydroquinone, resorcinol, 4,4'-dihydroxydiphenyl, bis(4-hydroxyphenyl) sulfide, bis(4-hydroxyphenyl) sulfone, bis(3,5-dimethyl-4-hydroxyphenyl) methane, bis(3,5-dimethyl-4-hydroxyphenyl) sulfone, 1,1-bis(3,5-dimethyl-4-hydroxyphenyl)-p/m-
 10 diisopropylbenzene, 1,1-bis(4-hydroxyphenyl)-1-phenyl ethane, 1,1-bis(3,5-dimethyl-4-hydroxyphenyl) cyclohexane, 1,1-bis(4-hydroxyphenyl)-3-methyl cyclohexane, 1,1-bis(4-hydroxyphenyl)-3,3-dimethyl cyclohexane, 1,1-bis(4-hydroxyphenyl)-4-methyl cyclohexane, 1,1-bis(4-hydroxyphenyl) cyclohexane, 1,1-bis(4-hydroxyphenyl)-3,3,5-trimethyl cyclohexane, 2,2-bis(3,5-dichloro-4-
 15 hydroxyphenyl) propane, 2,2-bis(3-methyl-4-hydroxyphenyl) propane, 2,2-bis(3,5-dimethyl-4-hydroxyphenyl) propane, 2,2-bis(4-hydroxyphenyl) propane ("bisphenol A"), 2,2-bis(3-chloro-4-hydroxyphenyl) propane, 2,2-bis(3,5-dibromo-4-hydroxyphenyl) propane, 2,4-bis(4-hydroxyphenyl)-2-methyl butane, 2,4-bis(3,5-dimethyl-4-hydroxyphenyl)-2-methyl butane, α,α' -bis(4-hydroxyphenyl)-o-
 20 diisopropyl benzene, α,α' -bis(4-hydroxyphenyl)-m-diisopropyl benzene ("bisphenol M"), α,α' -bis(4-hydroxyphenyl)-p-diisopropyl benzene and indane bisphenol, as well as optionally mixtures thereof.

25

Particularly preferred polycarbonates are the homopolycarbonate based on bisphenol A, the homopolycarbonate based on 1,1-bis(4-hydroxyphenyl)-3,3,5-trimethyl cyclohexane and the copolycarbonates based on the monomers bisphenol A and 1,1-bis(4-hydroxyphenyl)-3,3,5-trimethyl cyclohexane.

30

The bisphenols to be utilised according to the invention are reacted with carbonic acid compounds, in particular phosgene.

Polyester carbonates are obtained by reacting the bisphenols already mentioned, at least one aromatic dicarboxylic acid and optionally carbonic acid. Suitable aromatic dicarboxylic acids are, for example, orthophthalic acid, terephthalic acid, isophthalic acid, 3,3'- or 4,4'-diphenyl dicarboxylic acid and benzophenone dicarboxylic acids.

5 Up to 80 mol%, preferably approximately 20 to 50 mol%, of the carbonate groups in the polycarbonates may be replaced by aromatic dicarboxylic acid ester groups.

The average molecular weight \overline{M}_w of the polycarbonates according to the invention can be adjusted in known manner by means of chain terminators. The chain
10 terminators may be utilised in individual manner or as a mixture of different chain terminators.

Suitable chain terminators are, for example, monophenols and monocarboxylic acids. Suitable monophenols are, for example, phenol, p-chlorophenol, p-tert.-butyl
15 phenol, cumyl phenol or 2,4,6-tribromophenol as well as long-chain alkyl phenols such as 4-(1,1,3,3-tetramethylbutyl) phenol or monoalkyl phenols or dialkyl phenols, respectively, having a total of 8 to 20 C atoms in the alkyl substituents, such as, for example, 3,5-di-tert.-butylphenol, p-tert.-octylphenol, p-dodecylphenol, 2-(3,5-dimethylheptyl)phenol or 4-(3,5-dimethylheptyl)phenol. Suitable
20 monocarboxylic acids are for example benzoic acid, alkylbenzoic acids and halobenzoic acids.

Preferred chain terminators are phenol, p-tert.-butyl phenol, 4-(1,1,3,3-tetramethylbutyl)phenol and cumyl phenol.

25

The quantity of chain terminators is preferably between 0.25 and 10 mol%, in relation to the total of bisphenols used in each case.

The polycarbonates which are suitable according to the invention may be branched
30 in known manner, specifically preferably by the incorporation of trifunctional or higher than trifunctional branching agents. Suitable branching agents are, for

- 20 -

example, those such as have three or more phenolic groups or those such as have three or more carboxylic acid groups.

Suitable branching agents are, for example, phloroglucin, 4,6-dimethyl-2,4,6-tri-(4-hydroxyphenyl)-hept-2-ene, 4,6-dimethyl-2,4,6-tri(4-hydroxyphenyl) heptane, 1,3,5-tri(4-hydroxyphenyl) benzene, 1,1,1-tris-(4-hydroxyphenyl) ethane, tri(4-hydroxyphenyl) phenyl methane, 2,2-bis-[4,4-bis-(4-hydroxyphenyl)-cyclohexyl] propane, 2,4-bis-(4-hydroxyphenylisopropyl) phenol, 2,6-bis-(2-hydroxy-5'-methylbenzyl)-4-methyl phenol, 2-(4-hydroxyphenyl)-2-(2,4-dihydroxyphenyl) propane, hexa(4-(4-hydroxyphenylisopropyl) phenyl) terephthalic acid ester, tetra(4-hydroxyphenyl) methane, tetra(4-(4-hydroxyphenylisopropyl) phenoxy) methane and 1,4-bis-(4',4''-dihydroxytriphenyl) methyl) benzene as well as 2,4-dihydroxybenzoic acid, trimesic acid, cyanuric chloride, 3,3-bis(3-methyl-4-hydroxyphenyl)-2-oxo-2,3-dihydroindole, trimesic acid trichloride and α,α',α'' -tris-(4-hydroxyphenyl)-1,3,5-triisopropyl benzene.

Preferred branching agents are 1,1,1-tris(4-hydroxyphenyl) ethane, 3,3-bis(3-methyl-4-hydroxyphenyl)-2-oxo-2,3-dihydroindole and isatin bisresol.

The quantity of the branching agents which are optionally to be utilised is preferably from 0.05 mol% to 2 mol%, in relation to moles of bisphenols utilised.

The branching agents may, for example if the polycarbonate is prepared by the interfacial process, be introduced as an initial charge with the bisphenols and the chain terminators in the aqueous alkaline phase, or they may be added dissolved in an organic solvent, together with the carbonic acid derivatives. In the case of the transesterification process the branching agents are preferably dispensed together with the dihydroxy aromatics or bisphenols.

In order to prepare the polycarbonates by the interfacial process the bisphenols are dissolved in an aqueous alkaline phase, preferably sodium hydroxide solution. The chain terminators which are optionally necessary for the preparation of

copolycarbonates are dissolved, in quantities of from 1.0 to 20.0 mol% per mole bisphenol, in the aqueous alkaline phase or are added without dissolution to the latter in an inert organic phase. Phosgene is then passed into the mixer containing the remaining reaction constituents, and the polymerisation is carried out. After the reaction the organic phase which comprises the polycarbonate is separated from the aqueous phase and washed several times, and the polycarbonate is then isolated.

Organic solvents which are usable in the interfacial process are, for example, dichloromethane, the various dichloroethanes and chloropropane compounds, chlorobenzene and chlorotoluene. Dichloromethane and mixtures of dichloromethane and chlorobenzene are preferably utilised.

In the interfacial process the reaction may be accelerated by catalysts such as tertiary amines, N-alkyl piperidines or onium salts. Tributylamine, triethylamine and N-ethyl piperidine are preferably used.

The moulding compositions according to the invention may furthermore comprise suitable additives such as mould release agents, UV absorbers, stabilisers, lubricants, antistatic agents, fillers and/or reinforcing materials, antioxidants, pigments, dyes, and finely divided minerals. The additives are incorporated into the amorphous thermoplastic polymer in known manner by mixing polymer granules with the additives, followed by extrusion, or by mixing the solutions of the polymer with solutions of the additives, followed by evaporation of the solvents in known manner. The additives content of the thermoplastic moulding composition may be varied within broad limits and is dictated by the desired properties of the moulding composition. The total additive content of the moulding composition is preferably from 0 to 20 wt.%, still more preferably 0 to 5 wt.%, in relation to the weight of the moulding composition.

Examples of mould release agents are calcium stearate, zinc stearate, glycerol monostearate and pentaerythritol tetrastearate; preferred mould release agents are glycerol monostearate and pentaerythritol tetrastearate.

- 22 -

UV absorbers may be added to the moulding compositions, in particular when these are used for the production of mouldings for the construction sector, such as windows or sheets. Suitable UV absorbers are compounds such as are able to afford polycarbonate effective protection from UV light owing to their absorption capacity below 400 nm, and such as have a molecular weight of more than 370, preferably 500 or more. Such UV absorbers are described in EP 0 500 496 A1, for example.

Suitable stabilisers for amorphous thermoplastic polymers are, for example, stabilisers which comprise phosphines, phosphites or silicon, as well as further compounds described in EP 0 500 496 A1. Triphenyl phosphites, diphenylalkyl phosphites, phenyldialkyl phosphites, tris(nonylphenyl) phosphite, tetrakis(2,4-di-tert.-butylphenyl)-4,4'-biphenylene diphosphonite and triphenyl phosphite might be named as examples.

Examples of lubricants are hydrocarbons (for example paraffin oils, polyethylene waxes), alcohols (for example stearyl alcohol), carboxylic acids (for example lauric acid, palmitic acid, stearic acid), carboxylic acid amides (for example stearic acid amide, ethylenediamine bisstearyl amide), carboxylic acid esters (for example n-butyl stearate, stearyl stearate, glycerol monostearate, glycerol tristearate, pentaerythritol tetrastearate); preferred lubricants are carboxylic acid amides and carboxylic acid esters.

Examples of antistatic agents are cationic compounds (for example quaternary ammonium, phosphonium or sulfonium salts), anionic compounds (for example alkyl sulfonates, alkyl sulfates, alkyl phosphates, carboxylates in the form of alkali metal or alkaline earth metal salts), nonionic compounds (for example polyethylene glycol esters, polyethylene glycol ethers, fatty acid esters, ethoxylated fatty amines); preferred antistatic agents are nonionic compounds.

Preferred fillers are glass spheres, mica, silicates, quartz, talc, titanium dioxide or wollastonite. Preferred reinforcing materials are glass fibres or carbon fibres.

- 23 -

5 The moulding compositions according to the invention may be prepared by mixing the respective constituents in known manner and melt-compounding or melt-extruding in conventional units such as internal mixers, extruders and twin-screw units at temperatures of from approximately 200°C to 330°C.

10 The individual constituents can be mixed in known manner in both successive and also simultaneous manner, specifically both at room temperature and also at elevated temperature.

15 The invention also provides moulded bodies produced with the moulding compositions according to the invention. The moulding compositions may be utilised for the manufacture of solid plastic sheets and so-called cellular sheets or multi-wall sheets (twin-wall sheets). These moulded bodies are produced by extrusion or co-extrusion. The sheets also include those such as have an additional outer layer on one side, which is embodied, for example, to be particularly weather-resistant. Mouldings such as housings of all kinds for electrical and mechanical apparatus such as domestic appliances like juice presses, coffee machines, mixers and office machines as well as mouldings for automotive construction can be
20 obtained by injection moulding. Owing to their good electrical properties, the mouldings can moreover be utilised in the electrotechnical field. The moulded bodies may be produced in known manner by extrusion or injection moulding. Other moulded bodies which are furthermore considered are films.

25 The moulded bodies can furthermore be produced with the use of scrap (recycled product) from the moulding compositions according to the invention. For this purpose scrap such as housing waste or sheet waste made of the moulding composition according to the invention is comminuted in suitable manner, for example by shredders, and is then processed in known manner, either as such or with
30 the admixture of non-recycled moulding composition, to produce moulded bodies.

The invention is further explained by means of embodiment Examples.

Examples**a) Preparation of the moulding compositions**

- 5 The polycarbonate moulding compositions indicated in Table 1 were prepared by extruding bisphenol A-based aromatic polycarbonate Makrolon® 2808, natural, from Bayer AG which has an average molecular weight (M_w determined by GPC, PC standard) of 30,000, at 300°C on a twin-screw extruder with the indicated quantities of additives, followed by granulation. Sachtoperse® HU-N Spezial from
10 Sachtleben Chemie GmbH, 47184 Duisburg, was used as the barium sulfate. This had an average particle size of from 100 to 150 nm (incorporated in the polycarbonate by compounding). The particle size was determined by ultracentrifuging as described by Langer, H., "Particle and Particle Size Characterization", Vol. 12, p. 148, 1995. Glycerol monostearate (GMS) or
15 pentaerythritol tetrastearate (PETS) was used as the mould release agent. Hostaflon® (TF 2021) from Hoechst AG was utilised as the polytetrafluoroethylene. The granules were dried at from 100 to 120°C in a vacuum drying cabinet.

Table 1**Composition of the moulding compositions**

Example	Polycarbonate wt. %	C ₄ F ₉ SO ₃ K wt. %	BaSO ₄ wt. %	GMS wt. %	PETS wt. %	Saccharine wt. %	Hostaflon® TF 2021 wt. %
1	99.45	0.08	-	-	-	-	-
2	99.92	0.08	-	-	0.47	-	-
3	99.37	0.08	0.08	-	0.47	-	-
4	99.81	0.12	0.06	0.0003	-	0.0003	-
5	99.25	0.50	0.25	0.0012	-	0.0012	-
6	99.24	0.38	0.38	0.0019	-	0.0019	-
7	99.00	0.33	0.66	0.0034	-	0.0034	-
8	98.50	0.25	1.24	0.0062	-	0.0062	-
9	99.27	0.20	-	-	0.47	-	0.06
10	98.47	0.20	0.80	-	0.47	-	0.06

5 **b) Flame retardancy behaviour**

10 The granules obtained in Examples 1 to 10 were injection moulded on an injection moulding machine at a melt temperature of 300°C to form test bars having edges 127 x 12.7 mm long and layer thicknesses as indicated in Table 2. The test bars then underwent a flammability test in accordance with regulation UL-94 (Flammability of Solid Plastic Samples, Underwriters Laboratories, Northbrook, Illinois, USA) and were allocated to UL-94 flammability classes V0, V1 and V2, or "Fail", respectively. A bar test in accordance with regulation UL-94 5V (Flammability of Solid Samples) was furthermore carried out in respect of the moulding compositions prepared in Examples 9 and 10. The results of the flammability tests in respect of the

15 moulding compositions of Examples 1 to 10 are shown in Table 2.

- 26 -

Table 2**Flame retardancy behaviour**

Example	Layer thickness	UL-94 test	UL-94 5V bar test	UL-94 VTM
1	3.2 mm	V0	-	-
	2.6 mm	V0	-	-
	2.4 mm	V0	-	-
2	3.2 mm	V0	-	-
	2.6 mm	V1	-	-
	2.4 mm	V2	-	-
3	3.2 mm	V0	-	-
	2.6 mm	V0	-	-
	2.4 mm	V0	-	-
4	0.25 mm	-	-	VTM 0
5	2.4 mm	V0	-	-
6	2.4 mm	V0	-	-
6 (recycled product)	2.0 mm	V0	-	-
7	2.4 mm	V0	-	-
8	2.4 mm	V0	-	-
9	2.8 mm	-	Fail	-
	0.8 mm	V0	-	-
10	2.8 mm	-	Pass	-
	2.4 mm	-	Pass	-
	0.8 mm	V0	-	-
10 (recycled product)	0.8 mm	V0	-	-

5

- = test not carried out

- 27 -

Examples 1 to 3 in Table 2 show that the addition of nanoscale barium sulfate in particular in the presence of mould release agents such as PETS has a markedly improved flame-retardant effect at a layer thickness of 2.4 mm.

5 The moulding composition prepared in Example 4 with the addition of potassium perfluorobutane sulfonate and barium sulfate in the presence of GMS as the mould release agent and saccharine shows an excellent flame retardancy behaviour, even after processing to a film 0.25 mm thick, and was classified into class VTM 0 following the UL-94 VTM flame impingement test (flammability of films). A
10 further advantage of the films produced in Example 4 is their transparency.

Examples 5 to 8 in Table 2 furthermore show that the addition of nanoscale barium sulfate even in the presence of GMS as a mould release agent shows an excellent flame-retardant effect, and all these Examples were classified as V0 in accordance
15 with UL-94, at a layer thickness of 2.4 mm.

Examples 5 and 6 show that the fire-retardant effect of potassium perfluorobutane sulfonate in conjunction with barium sulfate can be improved still further by the addition of fluorinated hydrocarbons such as Hostaflon® TF 2021. The moulding
20 compositions of Examples 5 and 6 are classified into UL-94 flammability class V0 even at a layer thickness of 0.8 mm. Examples 5 and 6 furthermore show that the fire behaviour in accordance with the 5V bar test can be improved by the addition of nanoscale barium sulfate. Furthermore, the recycled products produced by shredding the moulding compositions according to Examples 6 and 10 and injection moulding
25 them again pass the UL-94 test at a thickness of 2.0 or 0.8 mm, with the score V0 (see Table 2).

The notched impact strength of the moulding composition from Example 10 in accordance with ISO 180-4a at room temperature was around 90 kJ/m², both before
30 and after recycling.

c) Transparency behaviour

The transparency of the moulding compositions prepared in accordance with Examples 1 to 3 was determined in accordance with ASTM D 1003 regulation by means of the Haze-Gard Plus apparatus from Byk-Gardner GmbH, D-82538 Geretsried, Germany in respect of a layer thickness of 4 mm. The results of the transparency test are given in Table 3.

Table 3 Transparency behaviour

Example	Layer thickness	Transmission in accordance with ASTM D 1003
1	4 mm	92.8
2	4 mm	93.0
3	4 mm	90.6

The transparency tests show that the addition of nanoscale barium sulfate as a flame retardancy reinforcing agent in a quantity of 0.08 wt.%, in relation to the total weight of the moulding composition, has no appreciable influence on the transparency of the moulding compositions. With a transmission of 90.6 at a layer thickness of 4 mm, the moulding composition according to the invention from Example 3 has an excellent transparency profile.

Claims

1. Thermoplastic moulding composition which comprises an amorphous thermoplastic polymer and at least one flame retardant, characterised in that the moulding composition includes at least one alkaline earth metal sulfate and/or one oxide having in each case an average particle size of up to 400 nm and that the flame retardant comprises fully or partially fluorinated sulfonic acid salts corresponding to the general formula (I)



in which

R is a straight-chain or branched aliphatic radical having 1 to 30 carbon atoms or an aromatic radical having 6 to 30 carbon atoms which may be fully or partially halogenated,

M is any cation, and

n is a number corresponding to the valency of M.

2. Moulding composition according to claim 1, characterised in that the alkaline earth metal sulfate and/or oxide is selected from among $MgSO_4$, $CaSO_4$, $SrSO_4$, $BaSO_4$, GeO_2 , PbO , PbO_2 , CeO_2 , Ce_2O_3 , SnO , SnO_2 , ZnO , TiO_2 , SiO_2 , ZrO_2 , HfO_2 , Al_2O_3 , Sc_2O_3 , La_2O_3 and Fe_2O_3 .

3. Moulding composition according to claim 2, characterised in that the alkaline earth metal sulfate is barium sulfate.

4. Moulding composition according to claim 1, characterised in that the alkaline earth metal sulfate and/or oxide in each case has an average particle size of up to 200 nm, in particular approximately 5 to 40 nm.

- 30 -

5. Moulding composition according to claim 1, characterised in that the alkaline earth metal sulfate and/or oxide is present in a quantity of from 0.001 to 5.0 wt.%, in particular up to 2.0 wt.%, in relation to the total weight of the moulding composition.

6. Moulding composition according to claim 1, characterised in that the quantity of the flame retardant utilised is from 0.001 to 5.0 wt.%, in particular 0.05 to 0.5 wt.%, in relation to the total weight of the moulding composition.

7. Moulding composition according to claim 1, characterised in that the moulding composition comprises additionally at least one fluorinated hydrocarbon such as polytetrafluoroethylene.

8. Moulding composition according to claim 7, characterised in that the quantity of the fluorinated hydrocarbons is from 0.001 to 0.5 wt.%, in particular 0.01 to 0.1 wt.%, in relation to the total weight of the moulding composition.

9. Process for the preparation of a moulding composition according to one of claims 1 to 8, characterised in that flame retardant and alkaline earth metal sulfate and/or oxide as well as optionally fluorinated hydrocarbon are mixed with the thermoplastic polymers which are to be equipped to be flame-resistant.

10. Moulded body produced with the use of the thermoplastic moulding composition according to one of claims 1 to 8.

11. Moulded body according to claim 10, characterised in that it is obtainable with the use of a recycled product made of the moulding composition according to one of claims 1 to 8.

- 31 -

12. Process for the production of a moulded body according to claim 10, characterised in that the moulding composition is processed by extrusion or injection moulding to form moulded bodies.
13. Use of an alkaline earth metal sulfate and/or an oxide having in each case an average particle size of up to 400 nm in thermoplastic moulding compositions prepared from amorphous polymers in order to increase the flame-retardant effect of flame retardants.




0943760-0004

POWER OF ATTORNEY: I, a named inventor, I hereby appoint the following attorney(s) and this application and to transact all business in the Patent and Trademark Office connection

JOSEPH C. GIL, Patent Office Registration Number 26,602 ARON PREIS, Patent Office Registration Number 29,426
LYNDANNE M. WHALEN, Patent Office Registration Number 29,457 THOMAS W. ROY,
Patent Office Registration Number 29,582 RICHARD E. L. HENDERSON, Patent Office Registration Number 31,619
GODFRIED R. AKORLI, Patent Office Registration Number 28,779 N. DENISE BROWN, Patent Office
Registration Number 36,097 NOLAND J. CHEUNG, Patent Office Registration Number 39,138
DIDERICO VAN EYL, Patent Office Registration Number 38,641 CAROLYN M. SLOANE, Patent Office
Registration Number 44,339 JAMES R. FRANKS, Patent Office Registration Number 42,552
JACKIE ANN ZURCHER, Patent Office Registration Number 42,251
RAYMOND J. HARMUTH, Patent Office Registration Number 33,896

all of Bayer Corporation, Pittsburgh, Pennsylvania 15205-9741

Send Correspondence To: Direct Telephone Calls To:
Patent Department
Bayer Corporation (412) 777-2349
100 Bayer Road
Pittsburgh, Pennsylvania 15205-9741

FULL NAME OF SOLE OR FIRST INVENTOR Axel Brenner		INVENTOR'S SIGNATURE 	DATE 12-07-2001
RESIDENCE D 40479 Düsseldorf, Germany DEX		CITIZENSHIP German	
POST OFFICE ADDRESS c/o BAYER AKTIENGESELLSCHAFT, D 51368 Leverkusen, Germany			
FULL NAME OF SECOND INVENTOR Walter Köhler		INVENTOR'S SIGNATURE 	DATE 12-07-2001
RESIDENCE D 47239 Duisburg, Germany DEX		CITIZENSHIP German	
POST OFFICE ADDRESS c/o BAYER AKTIENGESELLSCHAFT, D 51368 Leverkusen, Germany			
FULL NAME OF THIRD INVENTOR Martin Döbler		INVENTOR'S SIGNATURE 	DATE 12-7-2001
RESIDENCE D 40593 Düsseldorf, Germany DEX		CITIZENSHIP German	
POST OFFICE ADDRESS c/o BAYER AKTIENGESELLSCHAFT, D 51368 Leverkusen, Germany			
FULL NAME OF FOURTH INVENTOR		INVENTOR'S SIGNATURE	DATE
RESIDENCE		CITIZENSHIP	
POST OFFICE ADDRESS			
FULL NAME OF FIFTH INVENTOR		INVENTOR'S SIGNATURE	DATE
RESIDENCE		CITIZENSHIP	
POST OFFICE ADDRESS			
FULL NAME OF SIXTH INVENTOR		INVENTOR'S SIGNATURE	DATE
RESIDENCE		CITIZENSHIP	
POST OFFICE ADDRESS			
FULL NAME OF SEVENTH INVENTOR		INVENTOR'S SIGNATURE	DATE
RESIDENCE		CITIZENSHIP	
POST OFFICE ADDRESS			

COMBINED DECLARATION AND POWER OF ATTORNEY

ATTORNEY DOCKET NO

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name. I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought

on the invention entitled

"FLAME-RESISTANT THERMOPLASTIC MOULDING MATERIAL"

the specification of which is attached hereto,

or was filed on **February 11, 2000**

as a PCT Application Serial No. **PCT/EP00/01117**

I hereby state that I have reviewed and understand the contents of the above-identified specification, including the claims.

I acknowledge the duty to disclose information which is material to the patentability of this application in accordance with Title 37, Code of Federal Regulations, §1.56.

I hereby claim foreign priority benefits under Title 35, United States Code, §119 of any foreign application(s) for patent or inventor's certificate listed below and have also identified below any foreign application for patent or inventor's certificate having a filing date before that of the application on which priority is claimed:

Prior Foreign Application(s), the priority(ies) of which is/are to be claimed:

✓ 199 07 831.9	Germany	February 24, 1999
(Number)	(Country)	(Month/Day/Year Filed)

I hereby claim the benefit under Title 35, United States Code, §120 of any United States application(s) listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States application in the manner provided by the first paragraph of Title 35, United States Code, §112, I acknowledge the duty to disclose the material information as defined in Title 37, Code of Federal Regulations, §1.56 which occurred between the filing date of the prior application and the national or PCT international filing date of this application:

(Application Serial No.)	(Filing Date)	(Status)
		(patented, pending, abandoned)

(Application Serial No.)	(Filing Date)	(Status)
		(patented, pending, abandoned)

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Le A 33 042-US

00943700 004704

DK